

mdm nt sp. z o.o. ul. Bestwińska 143 43-346 Bielsko-Biała, Poland phone: +48 33 47 94 402 fax: +48 33 47 94 513 e-mail: office@mdmnt.com www.mdmnt.com

## Technical data sheet

# mdm ViBest Super Pro

### Notes:

Extremely durable, flexible (film TPU - DAXALL<sup>®</sup>) repair tape for membranes and construction foils. Used for repairing damages caused during the laying of the foil and making seals in the places where the roof accessories pass through the roof slope.

#### Material:

Waterproof functional TPU DAXALL® film, covered with a layer of technical glue.

Dimensions:

Roll dimensions: 50 mm x 25 m



Tape construction:	Liner:	PE-paper, white
		both sides silicone coated
		weight: 120 g/m
	Adhesive:	pure acrylate
		coat weight: 185 g/m
	Carrier:	TPU-f ilm, black
		thickness: 100 μm
Tape thickness:	approx. 0,27 µm excl. liner	
Adhesion [N/25mm]	steel	40*
In accordance to AFERA 5001		measure with a bonded 50 µm PET-film
Temperature Resistance	- 40°C to +80°C	

#### Storage.

This product should be stored at ambient temperatures of around 20°C, avoiding wide temperature fluctuations and direct sunlight. The storage environment should have a relative humidity of approx. 50%. In ideal storage conditions, the shelf life of this material will be approx. 12 months from the delivery date. With in this 12 month period, when stored correctly, there should be no deterioration of the products published performance specification.

**Product use.** All statements, technical info contained herein are based on lab testing, we believe to be reliable. In reality, many factors beyond our control can affect and influence the use and performance of our products an any particular application. Since these factors are uniquely within the users knowledge and control, it is essential that the user evaluate the product to determine its suitability for purpose. mdm NT will not be liable for any loss or damage arising, whether direct or indirect, special, incidental or consequential.

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using. Our product that it is suitable for the material for intend application. For technical assistance please call our product specialists. The data and statements are Intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale, a copy is available on request.

Bielsko-Biała, 06. 09. 2019